



## Product Technical Data / Product Type: 2734

Fabric Type	
Needlefelt, Thermal Bonded, Laminated Nonwoven	

Composition	
Polyester	
Polypropylene	
SAF™	
Polyester / Polypropylene Laminate, Top and Bottom	

Physical Characteristics	
Total Weight (g/m <sup>2</sup> )	260
Thickness (mm)	2.0

Absorbency (0.9% Saline)	
Absorbent capacity (g/g)	10
Absorbent volume (g/m <sup>2</sup> )	>2,600

Absorbency (DM water)	
Absorbent capacity (g/g)	18
Absorbent volume (g/m <sup>2</sup> )	>4,600

All tests are carried out in accordance with standard protocols.

This document does not constitute a specification for the above material, it is provided as an indication only.

### Technical Absorbents Ltd.

1 Moody Lane, Great Coates, Grimsby,  
North East Lincolnshire, DN31 2SS. United Kingdom

☎ +44 (0)1472 245200 ✉ info@exploreSAF.com

exploreSAF.com

a Technical Absorbents product